



V2100 Ultra Glamour Clear


Description:

The V2100 Ultra Glamour Clear is a top of the line high solid, high build clearcoat with excellent vertical stability with a glamour finish.

Suitable Substrates:

GenRock basecoat

Gen₂0 basecoat



Mix 2:1 with any of the following hardeners:

- VC60 2K Fast Hardener
- VC70 2K Medium Hardener
- VC80 2K Slow Hardener

Potlife: 4h at 20°C (68°F)



20-22s / # 2 Zahn @ 68°F



Compliant 1.3 – 1.5 mm (2 spray passes)
2.5 bar inlet pressure (36 PSI)
0.8-1.0 Mil per full coat



HVLP 1.3 – 1.5 mm (2 spray passes)
0.7 bar atomization pressure (10 PSI)
0.8-1.0 Mil per full coat



Wait 12-14 min before increasing temperature
Bake 20 min at 60 °C (140°F) panel temperature



Short Wave 8 min
The object should be maintained at greater than 60cm from source.



Wear suitable protection



V2100 Ultra Glamour Clear

VOC: **Regulatory VOC 505.2 gr/lit (4.2 lbs/gal)**
 Regulatory VOC ready to spray < 498.5 gr/lit (4.15 lbs/gal)

Specific Gravity: 0.966 kg/lit (8.04 lbs/gal)

Solids Content: 46.0 – 47.0 % by weight RFU

Coverage: 700 ft²/gal at 1 dry mil dry film thickness (theoretical)

SDS: See the safety data sheet.